

**TECHNICAL DATA SHEET** 

# **EURO CLEARCOAT**

Two-component urethane clearcoat characterized by high content of solids. High hardness, resistance to: weather conditions, UV rays and stone impact. Coating does not chip off even with strong strokes of stones. Has excellent gloss, excellent flow and elasticity which guarantees the perfect look of painted coating.

PACKAGING		
CODE	DESCRIPTION	PIECES PER BOX
SPC-500	Euro Clearcoat 5 liter	4
SPH-571 SPH-572 SPH-573	Euro Ultra Hardner Slow 2.5 liter Euro Ultra Hardner Medium 2.5 liter Euro Ultra Hardner Fast 2.5 liter	4





#### **INFORMATION**



100 parts Euro Clearcoat,50 parts Euro Ultra hardener,0 - 5 parts Reducer.



Two full layers with evaporation.

Spray gun\*. Nozzle opening with the pneumatic

method: **1.3 - 1.4 mm**.

Pressure – HVLP: **2 - 2,5 bar**\*.

 $^{\ast}$  Use high pressure equipment and HVLP. Pressure as recommended by the gun manufacturer.



Drying time 20°C:

Dust free: **20 min** Through dry: **1 h** 

Drying time  $40^{\circ}$ C: prior to assembly: **15 min** Drying time  $60^{\circ}$ C: prior to assembly: **25 - 30 min** 



Evaporation between the layers (20°C, 65% H.R.): **10 min**.



Drying IR: ~5 min.

#### **SURFACE PREPARATION**

Clean surfaces with silicon remover.

# **SPRAY VISCOSITY IN 20°C**

16-17 s DIN Cup 4 mm

### **POT LIFE**

40 min

#### THICKNESS OF DRY COATING

~40-70 μm

#### **RECOMMENDED SIZES OF PAINT STRAINERS**

125-190 μm

## VOC

2004/42/CE/II,B/e(840)

## DATE OF MINIMUM DURABILITY

SPC-500: 24 months (in the original unopened package) SPH-571: 12 months (in the original unopened package) SPH-572: 12 months (in the original unopened package) SPH-573: 12 months (in the original unopened package)